

TEST REPORT

Company Name Sample Description

Identifiers

TESTED FOR

List tests

Report #: 2009-YYY Month XX, 2009

3612 3rd PI. NW, Rochester, MN 55901 • Phone: 507-292-0230 • Fax: 507-292-0698 • www.microstatlabs.com



SUMMARY

Three lots of test samples were submitted for testing to Specification XXXXXX. The samples all meet the defined specification limits.

EXPERIMENTAL AND DISCUSSION

All testing was carried out per the methods defined in Method XXXX of Specification XXXXX. All data is included below in Tables X, Y & Z.

Surface Resistance Data sting per ANSI/ESD STM11.							
	Surface						
Sample #	Resistance						
1	4.23 x 10 ¹⁰ Ω						
2	7.40 x 10 ¹⁰ Ω						
3	4.39 x 10 ¹⁰ Ω						
4	8.34 x 10 ¹⁰ Ω						
5	5.69 x 10 ¹⁰ Ω						
6	3.04 x 10 ¹⁰ Ω						
Average	4.15 x 10 ¹⁰ Ω						
St. Dev.	3.28						
Median	4.23 x 10 ¹⁰ Ω						
Minimum	1.80 x 10 ¹⁰ Ω						
Maximum	8.34 x 10 ¹⁰ Ω						

Table X Te 11

Table X Static Discharge Shielding Data Summary

	12% R.H. Data	50% R.H. Data			
Average	17.66 nJ	19.41 nJ			
St. Dev.	2.36 nJ	3.60 nJ			
Min	11.87 nJ	13.56 nJ			
Max	21.95 nJ	27.37 nJ			



Inside Surface										
Bag #	+5000V to +50V				-5000V to -50V					
1	0	0	0	0	0	0	0	0	0	0
2	0	0	0	0	0	0	0	0	0	0
3	0	0	0	0	0	0	0	0	0	0
4	0	0	0	0	0	0	0	0	0	0
5	0	0	0	0	0	0	0	0	0	0
Outside Surface										
Bag #	+5000V to +50V			-5000V to -50V						
1	0	0	0	0	0	0	0	0	0	0
2	0	0	0	0	0	0	0	0	0	0
3	0	0	0	0	0	0	0	0	0	0
4	0	0	0	0	0	0	0	0	0	0
5	0	0	0	0	0	0	0	0	0	0

Table Z Static Decay Test Data



EQUIPMENT USED FOR ELECTRICAL TESTING

Surface Resistance Measurements: Keithley Model 6517a Electrometer/High Resistance Meter ETS Model 803B Resistance Probe ETS Model 809 Surface Resistance Verification Fixture

Static Discharge Shielding Measurements:

ETS Model 811/412 Electrostatic Discharge Unit/Shielding Bag Tester Tektronix TDS 520A Digital Oscilloscope.

Static Decay Time Measurements: TREK Model 341 ElectroStatic Voltmeter KeyTek MZ-15 ESD Simulator Novx Data Acquisition Software

The results provided in this report are accurate within the limits appropriate to each test standard. The results of this report are statistically significant only to the samples submitted for testing. MicroStat Laboratories/River's Edge Technical Service, Inc. has no controls, and assumes no responsibility for the tested product's functionality or use. This report shall not be reproduced, except in full, without written permission from River's Edge Technical Service, Inc.

Carl & nentry

Carl E Newberg

Date